

# COLPHENE 3000

TECHNICAL DATA SHEET 151127SCANE

(supersedes 140121SCAN1E)



WATERPROOFING

APPLICATIONS

FOUNDATIONS

## DESCRIPTION

**COLPHENE 3000** is a self-adhesive waterproofing membrane composed of SBS modified bitumen and a tri-laminated woven polyethylene facer. The underface is covered with silicone release film.

**COLPHENE 3000** is design for foundation walls and other below grade vertical surfaces.

## RECOMMENDED SUBSTRATES

This product can be used on most building surfaces, such as masonry, concrete and wood.

## SURFACE PREPARATION

Using one of **ELASTOCOL STICK** primer is recommended before the installation of **COLPHENE 3000** membrane. The substrate should be clean, sound, free of excess water and loose materials, grease and any contaminants, which may compromise the performance of the product.

## INSTALLATION

### SELF-ADHESIVE

**COLPHENE 3000** membrane must be adhered to support by peeling off the silicone release film.

Side lap joints must be a minimum of 75 mm (3 in) and end lap joints must be a minimum of 150 mm (6 in).

Once installed, a pressure must be applied over the whole surface using a membrane roller to ensure good contact.

The uppermost edge of the membrane shall be mechanically fastened using termination bars and sealed with **SOPRAMASTIC**.

Application temperatures: Winter grade: -10 to 10°C (14 to 50°F)  
Summer grade: 10 to 50°C (50 to 122°F)

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

## PACKAGING

Specifications	COLPHENE 3000
Thickness	1.5 mm (60 mil)
Dimensions	1 x 18.7 m (3.3 x 61 pi)
Weight	1.5 kg/m <sup>2</sup> (0.3 lb/ft <sup>2</sup> )
Selvedge width	75 mm (3 in)
Surface	Tri-laminated woven polyethylene
Underface	Silicone release film
Qty/pal	30

(All values are nominal)



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

NOTE : SOPREMA INC. may modify the composition and/or utilization of its products without prior notice.

TDS\_COLPHENE\_3000.indd

# COLPHENE 3000

TECHNICAL DATA SHEET 151127SCANE

(supersedes 140121SCAN1E)



WATERPROOFING

APPLICATIONS

FOUNDATIONS

## PROPERTIES

Properties	Standards	COLPHENE 3000
Tensile strength, MD/XD	ASTM D5147	11.3 / 15.4 kN/m (64 / 88 lb/in)
Tensile strength, MD/XD	ASTM D412	11.2 / 13.1 MPa (1624 / 1900 lb/in <sup>2</sup> )
Ultimate elongation, MD/XD	ASTM D412	88 / 55 %
Ultimate elongation, MD/XD	ASTM D5147	40 / 25 %
Elongation of rubberised asphalt	ASTM D5147	> 1000 %
Flexibility at cold temperature	ASTM D5147	-35°C (-31°F)
Static puncture	ASTM E154	747 N (168 lb)
Static puncture	ASTM D5602	400 N (90 lb)
Tear resistance, MD/XD	ASTM D5601	375 / 400 N (84 / 90 lb)
Lap adhesion	ASTM D1876	2000 N/m (11.4 lb/in)
Water absorption	ASTM D5147	0.1 % max
Peel resistance	ASTM D903	3500 N/m (20 lb/in)
Water vapour permeance	ASTM E96 (Procedure B)	0.49 ng/Pa·s·m <sup>2</sup> (0.0086 perm)
Crack cycling at -32°C (25.6°F), 100 cycles	ASTM C836	Unaffected
Resistance to hydrostatic head	ASTM D5385	114 m min. (374 ft)
Adhesion strength to concrete - Not primed - Combined with primer	ASTM D1000	560 N/m (3.2 lb/in) 1650 N/m (9.4 lb/in)

For CCMC product evaluation see CCMC Evaluation listing #13560-R  
(All values are nominal)

## STORAGE AND HANDLING

Rolls must be stored upright, with the selvedge side on top. If the product is stored outdoors, cover them with an opaque protective cover after removal of the delivery packaging.



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

NOTE : SOPREMA INC. may modify the composition and/or utilization of its products without prior notice.

TDS\_COLPHENE\_3000.indd